



SPECIAL
ASPHALT PRODUCTS
Sustainable Pavement Solutions



ALT - 651 Flex Crac™

A Cold Pour Crack Sealer

For Asphalt Surfaces (Exterior Use Only)

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.

GENERAL: A rubberized asphalt emulsion with greater flexibility designed for sealing narrow pavement cracks up to 1" in width, in asphalt and concrete surfaces. It has resilient characteristics that can allow self-threading or memory. It has excellent flow properties and no pinholing. It is ready to use on roadways, parking lots, airports, athletic courts, driveways, traffic safety islands, playgrounds and walkways.

SURFACE

PREPARATION: Surface must be dry and free from all loose material, dirt and dust. Oil contaminated cracks can be treated with Allstates' Poly Oil Sil® (ALT - 602) to improve adhesion.

APPLICATION: Mix well before using. Use as is. Fill cracks completely. Can be applied with a pour pot or suitable crack sealing machine. Scrape excess from surfaces (use rubber squeegee), and allow to cure completely before sealing with a mechanical applicator. To promote adhesion to coal tar or asphalt emulsion type pavement sealer, sprinkle silica sand (lightly) before it sets up, but not mandatory. If necessary, sprinkle silica sand to avoid tracking when climate conditions are extremely hot.

COVERAGE

PER GALLON: Indefinite. For estimation purposes – up to 80 linear feet of 1/2" X 1/2" depth cracks.

CAUTION: **KEEP FROM FREEZING.** Do not use when rain is in forecast, when surface is wet or when temperature is below 50°F. Wash tools in water. Use a paint thinner if material has dried. Do not store in direct sunlight or where temperatures exceed 100°F. Container should be closed when not in use. Keep out of the reach of children. Wherever low temperature flexibility is required (due to expansion and contraction) use Allstates' Super-Flex® (ALT - 654).

PACKAGING: 1 gallon jugs, 5 gallon pails and 55 gallon drums.

Material Specifications:	Requirements:
Weight per Gallon, @ 77°F, ASTM D1010, (lbs).....	9.20 – 9.60
Nonvolatile %, ASTM D2939	68.00
Viscosity @ 77°F, ASTM D562 (Kreb's Stormer Unit).....	85 –95
Penetration (0.1mm), ASTM D5	50 - 60
Drying Time (minutes) 1/4" X 1/4" @ 77°F & 50% RH	30 min.
Std. Spec. for Emulsified Asphalt	
AASHTO Designation M140 – 70	meets spec.
ASTM Designation D977 – 73 & D244	meets spec.

1-800-953-6490 toll free • www.specialasphalt.com

PORTLAND, OR
 3537 NW Saint Helens Rd
 Portland OR 97210-1313
 Phone: 503.295.6490
 Fax: 503.295.2901

MEDFORD, OR
 5758 Crater Lake Ave
 Central Point OR 97502
 Phone: 503.295.6490
 Fax: 503.295.2901

SPOKANE, WA
 3117 E Everett Ave
 Spokane WA 99217-6617
 Phone: 509.489.5353
 Fax: 509.489.5408

SEATTLE, WA
 9243 M L King Jr Way S
 Seattle WA 98118-5314
 Phone: 206.722.1413
 Fax: 206.725.8626